

PRODUCT SPECIFICATION

SOLAR SALT COARSE – SODIUM CHLORIDE (NaCl)

PACIFIC SWIMMING POOL SALT		
COMPONENTS	SPECIFICATION	REGULATORY STANDARD
Sodium Chloride as NaCl - Minimum moisture free	Min. 99.5%	DSL
Moisture Content	Max 0.2%	DSL
Matter Insoluble in water (Other than Calcium Sulphate)	Max 0.05	DSL
Arsenic as As	Max 0.5 mg/kg	DSL
Cadmium as Cd	Max 0.5 mg/kg	DSL
Copper as Cu	Max 2.0 mg/kg	DSL
Lead as Pb	Max 2.0 mg/kg	DSL
Mercury as Hg	Max 0.1 mg/kg	DSL
Sulphate as Na ₂ SO ₄	Max 3000 mg/kg	DSL
Calcium as Ca	Max 600 mg/kg	DSL
Magnesium as Mg	Max 400 mg/kg	DSL
Additives:		
Additive 535 as Na ₄ Fe (CN) ₆	Max 14 mg/kg	DSL
Grain Size:		
Passing 5 mm	100%	DSL

Notes:

Test performed on incoming bulk shipment before processing.

GRADE DESCRIPTION:

Specifically prepared for chlorine generation pools fitted with salt chlorinators. Salt is ex stack, crushed, washed and kiln dried.

Recommended directions for use are printed on pack

BULK DENSITY:

Nominally: loose 1021g/ml, compacted 1.43g/ml

COMPLIANCE:

Free from known Allergens

Supplier is ISO 9001, FSC 22000 certified

PACKAGING

20kg/ Polyethylene Bag without liner